

Schlieper & Heyng
Technical Data Sheet

May 2007

Ferroxon[®] 480

Type: Red iron oxide pigment
Delivery form: Powder, packed in PE-Bags or Big Bags

Characteristics

Fe₂O₃-content: 97 – 99 % m/m
Al₂O₃-content: 0,5 - 1,0 % m/m
SiO₂-content: 0,5 - 1,0 % m/m
Matter volatile at 105 °C: ca. 0,5 % m/m
Oil adsorption: 26 g/100 g
pH-value: 4,0 – 7,0

Our technical advice – whether verbal, in writing or by way of trials – is given in good faith but without warranty. It does not release the customer from the obligation to test the products as to their suitability for the intended processes and uses. Our products are sold in accordance with the current version of our general conditions of sale and delivery.