

Ferroxon[®] 510

Type: Yellow iron oxide pigment, C.I. Pigment Yellow 42,
77492

Delivery form: Powder, packed in PE-bags of 25 kg

Characteristics

Fe₂O₃: 86 – 88 M.-%
Al₂O₃: 0,05 - 0,2 M.-%
SiO₂: 0,05 - 0,2 M.-%
Loss on ignition: 11,0 - 13,0 M.-%
Oil absorption: 46 g/100g
pH-value: 4 - 7

Our technical advice – whether verbal, in writing or by way of trials – is given in good faith but without warranty. It does not release the customer from the obligation to test the products as to their suitability for the intended processes and uses. Our products are sold in accordance with the current version of our general conditions of sale and delivery.