

Ferroxon[®] 618

Type:	Black iron oxide pigment
Form of delivery:	Powder, packed in PE-bags 25 kg or Big Bags

<u>Characteristics</u>		<u>Test methode</u>
Fe₃O₄-content:	90 - 95 M.-%	DIN ISO 1248
Matter volatile at 105 °C:	≤ 0,5 M.-%	DIN ISO 787-2
Water soluble content:	≤ 0,5 M.-%	DIN ISO 787-3
Loss on ignition:	≤ 1,0 M.-%	DIN ISO 4621
Oil absorption:	35 g/100 g	DIN ISO 787-5
pH-value:	5 – 8	DIN ISO 787-9
Sieving residue 46 µm-sieve:	≤ 0,1 M.-%	DIN ISO 787-7

Our technical advice – whether verbal, in writing or by way of trials – is given in good faith but without warranty. It does not release the customer from the obligation to test the products as to their suitability for the intended processes and uses. Our products are sold in accordance with the current version of our general conditions of sale and delivery.